Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-07-23-61 **Date: 24/06/2020**

: Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

: Sri. C.N.S Murthy, #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagar, Bangalore-560 079.

: EE(Project)/Ynk Zone/WO/16/18-19

: 20-06-20

: GF Roof Concrete

: 150X150X150 mm

: M25 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 24/06/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
GF Roof Concrete	M25	17/06/2020	24/06/2020	149.89 X 149.20 X 151.16	22363	**8.615**	532.5	23.8	22.9
GF Roof Concrete	M25	17/06/2020	24/06/2020	150.32 X 150.21 X 149.21	22580	**8.547**	511.0	22.6	
GF Roof Concrete	M25	17/06/2020	24/06/2020	149.40 X 149.82 X 150.92	22385	**8.687**	497.1	22.2	

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-07-23-61** **Date: 15/07/2020**

: Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

: Sri. C.N.S Murthy, #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagar, Bangalore-560 079.

Reference : EE(Project)/Ynk Zone/WO/16/18-19

: 20-06-20

: GF Roof Concrete

Type /Size : 150X150X150 mm

grade/Age : M25 / 28 Days Compressive Strength

to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 15/07/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
GF Roof Concrete	M25	17/06/2020	15/07/2020	150.23 X 150.14 X 149.43	22557	**8.948**	620.8	27.5	27.6
GF Roof Concrete	M25	17/06/2020	15/07/2020	149.38 X 151.96 X 149.69	22699	**8.575**	600.0	26.4	
GF Roof Concrete	M25	17/06/2020	15/07/2020	150.99 X 151.94 X 150.82	22942	**8.789**	665.1	29.0	

CIVIL PRO BANGALORE Sig. Date.

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-07-23-61 **Date: 24/06/2020**

: Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

: Sri. C.N.S Murthy, #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagar, Bangalore-560 079.

Reference : EE(Project)/Ynk Zone/WO/16/18-19

: 20-06-20

ID : GF Roof Concrete

Type /Size : 150X150X150 mm

grade/Age : M25 / 7 Days Compressive Strength

to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 24/06/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
GF Roof Concrete	M25	17/06/2020	24/06/2020	151.20 X 150.98 X 149.00	22828	**8.615**	534.6	23.4	22.7
GF Roof Concrete	M25	17/06/2020	24/06/2020	151.04 X 151.77 X 150.90	22924	**8.547**	510.3	22.3	
GF Roof Concrete	M25	17/06/2020	24/06/2020	150.38 X 149.68 X 150.84	22510	**8.687**	502.0	22.3	

CIVIL PRO BANGALORE Sig. Date.

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-07-23-61** **Date: 15/07/2020**

: Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

: Sri. C.N.S Murthy, #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagar, Bangalore-560 079.

: EE(Project)/Ynk Zone/WO/16/18-19

: 20-06-20

: GF Roof Concrete

: 150X150X150 mm

: M25 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 15/07/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
GF Roof Concrete	M25	17/06/2020	15/07/2020	151.30 X 151.05 X 149.69	22854	8.948	634.5	27.8	27.7
GF Roof Concrete	M25	17/06/2020	15/07/2020	149.62 X 149.31 X 150.25	22339	8.575	590.0	26.4	
GF Roof Concrete	M25	17/06/2020	15/07/2020	150.93 X 151.17 X 151.93	22815	8.789	659.4	28.9	

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-07-23-61** **Date: 24/06/2020**

: Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

: Sri. C.N.S Murthy, #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagar, Bangalore-560 079.

Reference : EE(Project)/Ynk Zone/WO/16/18-19

Receipt : 20-06-20

ID : GF Roof Concrete

Type /Size : 150X150X150 mm

grade/Age : M25 / 7 Days Compressive Strength

to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Test : 24/06/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
GF Roof Concrete	M25	17/06/2020	24/06/2020	149.99 X 149.76 X 149.73	22462	**8.615**	534.2	23.8	22.9
GF Roof Concrete	M25	17/06/2020	24/06/2020	151.45 X 151.50 X 150.30	22945	**8.547**	509.1	22.2	
GF Roof Concrete	M25	17/06/2020	24/06/2020	150.85 X 149.44 X 151.73	22542	**8.687**	510.8	22.7	

CIVIL Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-07-23-61 **Date: 15/07/2020**

: Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

: Sri. C.N.S Murthy, #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagar, Bangalore-560 079.

Reference : EE(Project)/Ynk Zone/WO/16/18-19

Receipt : 20-06-20

ID : GF Roof Concrete

Type /Size : 150X150X150 mm

grade/Age : M25 / 28 Days Compressive Strength

to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Test : 15/07/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
GF Roof Concrete	M25	17/06/2020	15/07/2020	149.93 X 150.28 X 149.70	22532	**8.948**	627.7	27.9	27.3
GF Roof Concrete	M25	17/06/2020	15/07/2020	150.18 X 150.30 X 149.80	22572	**8.575**	587.8	26.0	
GF Roof Concrete	M25	17/06/2020	15/07/2020	151.55 X 151.70 X 150.52	22990	**8.789**	646.8	28.1	

CIVIL Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-07-23-61** **Date: 24/06/2020**

: Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

: Sri. C.N.S Murthy, #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagar, Bangalore-560 079.

: EE(Project)/Ynk Zone/WO/16/18-19

: 20-06-20

: GF Roof Concrete

: 150X150X150 mm

: M25 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 24/06/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
GF Roof Concrete	M25	17/06/2020	24/06/2020	149.15 X 150.37 X 149.89	22427	**8.615**	520.7	23.2	22.9
GF Roof Concrete	M25	17/06/2020	24/06/2020	150.87 X 151.02 X 149.93	22785	**8.547**	520.7	22.9	
GF Roof Concrete	M25	17/06/2020	24/06/2020	151.84 X 151.95 X 150.03	23072	**8.687**	523.0	22.7	

CIVIL Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-07-23-61

Date: 15/07/2020

: Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

: Sri. C.N.S Murthy, #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagar, Bangalore-560 079.

Reference : EE(Project)/Ynk Zone/WO/16/18-19

: 20-06-20

: GF Roof Concrete

Size : 150X150X150 mm

: M25 / 28 Days Compressive Strength

BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 15/07/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
GF Roof Concrete	M25	17/06/2020	15/07/2020	150.73 X 151.52 X 150.48	22838	**8.948**	632.6	27.7	27.3
GF Roof Concrete	M25	17/06/2020	15/07/2020	149.71 X 150.81 X 149.25	22578	**8.575**	589.8	26.1	
GF Roof Concrete	M25	17/06/2020	15/07/2020	151.62 X 150.38 X 149.26	22801	**8.789**	642.6	28.2	

CIVIL PRO Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

: 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-07-23-61** **Date: 24/06/2020**

: Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

: Sri. C.N.S Murthy, #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagar, Bangalore-560 079.

Reference : EE(Project)/Ynk Zone/WO/16/18-19

Receipt : 20-06-20

ID : GF Roof Concrete

Type /Size : 150X150X150 mm

grade/Age : M25 / 7 Days Compressive Strength

to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Test : 24/06/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
F Roof Concrete	M25	17/06/2020	24/06/2020	149.56 X 151.02 X 150.15	22586	**8.615**	521.2	23.1	22.8
F Roof Concrete	M25	17/06/2020	24/06/2020	149.61 X 151.68 X 151.14	22694	**8.547**	508.7	22.4	
F Roof Concrete	M25	17/06/2020	24/06/2020	149.64 X 149.15 X 151.32	22318	**8.687**	512.2	23.0	

CIVIL PRO BANGALORE Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 15/07/2020

: CP-2020-07-23-61

: Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

: Sri. C.N.S Murthy, #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagar, Bangalore-560 079.

: EE(Project)/Ynk Zone/WO/16/18-19

: 20-06-20

: GF Roof Concrete

: 150X150X150 mm

: M25 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 15/07/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
GF Roof Concrete	M25	17/06/2020	15/07/2020	149.87 X 151.65 X 151.07	22728	8.948	624.4	27.5	27.6
GF Roof Concrete	M25	17/06/2020	15/07/2020	149.97 X 150.11 X 151.21	22513	8.575	606.5	26.9	
GF Roof Concrete	M25	17/06/2020	15/07/2020	151.52 X 150.02 X 151.35	22730	8.789	645.4	28.4	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-07-23-61** **Date: 24/06/2020**

: Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

: Sri. C.N.S Murthy, #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagar, Bangalore-560 079.

's Reference : EE(Project)/Ynk Zone/WO/16/18-19

Receipt : 20-06-20

ID : GF Roof Concrete

Type /Size : 150X150X150 mm

grade/Age : M25 / 7 Days Compressive Strength

to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Test : 24/06/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
GF Roof Concrete	M25	17/06/2020	24/06/2020	149.36 X 151.54 X 150.80	22634	**8.615**	539.3	23.8	22.9
GF Roof Concrete	M25	17/06/2020	24/06/2020	150.80 X 151.03 X 149.69	22775	**8.547**	510.7	22.4	
GF Roof Concrete	M25	17/06/2020	24/06/2020	149.45 X 150.43 X 151.78	22482	**8.687**	502.7	22.4	

CIVIL PRO Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

	:	**CP-2020-07-23-61** **Date: 15/07/2020**
Name	:	Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.
	:	Sri. C.N.S Murthy, #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagar, Bangalore-560 079.
Reference	:	EE(Project)/Ynk Zone/WO/16/18-19
Receipt	:	20-06-20
ID	:	GF Roof Concrete
Type /Size	:	150X150X150 mm
grade/Age	:	M25 / 28 Days Compressive Strength
to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Test	:	15/07/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
GF Roof Concrete	M25	17/06/2020	15/07/2020	150.81 X 150.71 X 150.51	22728	**8.948**	630.1	27.7	27.7
GF Roof Concrete	M25	17/06/2020	15/07/2020	149.98 X 149.86 X 149.92	22476	**8.575**	596.2	26.5	
GF Roof Concrete	M25	17/06/2020	15/07/2020	151.87 X 150.31 X 151.04	22827	**8.789**	659.9	28.9	

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Report ID	:	**CP-2020-07-23-61** **Date: 24/06/2020**
Project Name	:	Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.
Agency	:	Sri. C.N.S Murthy, #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagar, Bangalore-560 079.
Customer's Reference	:	EE(Project)/Ynk Zone/WO/16/18-19
Date of Receipt	:	20-06-20
Customer ID	:	GF Roof Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	24/06/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	GF Roof Concrete	M25	17/06/2020	24/06/2020	151.43 X 149.87 X 150.57	22695	**8.615**	534.7	23.6	22.7
2	GF Roof Concrete	M25	17/06/2020	24/06/2020	150.77 X 149.72 X 150.81	22573	**8.547**	502.4	22.3	
3	GF Roof Concrete	M25	17/06/2020	24/06/2020	151.31 X 150.18 X 149.27	22724	**8.687**	503.5	22.2	

CIVIL PRO BANGALORE Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

ID	:	**CP-2020-07-23-61** **Date: 15/07/2020**
Name	:	Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.
	:	Sri. C.N.S Murthy, #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagar, Bangalore-560 079.
mer's Reference	:	EE(Project)/Ynk Zone/WO/16/18-19
Receipt	:	20-06-20
mer ID	:	GF Roof Concrete
Type /Size	:	150X150X150 mm
grade/Age	:	M25 / 28 Days Compressive Strength
nce to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
test	:	15/07/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
GF Roof Concrete	M25	17/06/2020	15/07/2020	149.73 X 150.83 X 149.35	22583	**8.948**	616.5	27.3	27.6
GF Roof Concrete	M25	17/06/2020	15/07/2020	151.97 X 150.59 X 151.60	22886	**8.575**	612.5	26.8	
GF Roof Concrete	M25	17/06/2020	15/07/2020	151.81 X 149.28 X 149.77	22662	**8.789**	651.5	28.7	

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 15/07/2020

ID	:	**CP-2020-07-23-61**
ject Name	:	Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.
ncy	:	Sri. C.N.S Murthy, #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagar, Bangalore-560 079.
tomer's Reference	:	EE(Project)/Ynk Zone/WO/16/18-19
e of Receipt	:	20-06-20
tomer ID	:	GF Roof Concrete
mple Type /Size	:	150X150X150 mm
mple grade/Age	:	M25 / 28 Days Compressive Strength
ference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
e of test	:	15/07/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	GF Roof Concrete	M25	17/06/2020	15/07/2020	151.46 X 149.85 X 151.47	22696	**8.948**	614.3	27.1	27.3
2	GF Roof Concrete	M25	17/06/2020	15/07/2020	150.42 X 149.89 X 150.55	22547	**8.575**	588.9	26.1	
3	GF Roof Concrete	M25	17/06/2020	15/07/2020	150.58 X 151.34 X 150.43	22789	**8.789**	651.2	28.6	

Sig.....
Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

ID : **CP-2020-07-23-61** **Date: 24/06/2020**

ject Name : Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

ncy : Sri. C.N.S Murthy, #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagar, Bangalore-560 079.

mmer's Reference : EE(Project)/Ynk Zone/WO/16/18-19

e of Receipt : 20-06-20

mmer ID : GF Roof Concrete

mple Type /Size : 150X150X150 mm

mple grade/Age : M25 / 7 Days Compressive Strength

erence to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

e of test : 24/06/2020

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
GF Roof Concrete	M25	17/06/2020	24/06/2020	149.18 X 150.00 X 151.42	22378	**8.615**	525.4	23.5	22.8
GF Roof Concrete	M25	17/06/2020	24/06/2020	149.32 X 150.68 X 149.79	22498	**8.547**	499.6	22.2	
GF Roof Concrete	M25	17/06/2020	24/06/2020	150.86 X 151.84 X 151.85	22906	**8.687**	519.0	22.7	

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 15/07/2020

ID : **CP-2020-07-23-61**

ject Name : Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

ncy : Sri. C.N.S Murthy, #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagar, Bangalore-560 079.

tomer's Reference : EE(Project)/Ynk Zone/WO/16/18-19

e of Receipt : 20-06-20

tomer ID : GF Roof Concrete

mple Type /Size : 150X150X150 mm

mple grade/Age : M25 / 28 Days Compressive Strength

ference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

e of test : 15/07/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	GF Roof Concrete	M25	17/06/2020	15/07/2020	151.33 X 149.03 X 149.32	22553	8.948	627.7	27.8	27.6
2	GF Roof Concrete	M25	17/06/2020	15/07/2020	151.99 X 151.66 X 149.73	23052	8.575	605.5	26.3	
3	GF Roof Concrete	M25	17/06/2020	15/07/2020	149.31 X 150.59 X 150.80	22484	8.789	648.4	28.8	

Sig.
Date.

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****